



LABORATORIO CERAMICO SEBASTIAN CARPI
 COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
 TEL: 964 208 583 - FAX: 964 202 594
 www.laboratoriocarpi.com



TEST REPORT

PETITIONER: VIDREPUR, S.A.
 ADDRESS: C/ Comercio, nº 4
 CITY: ALMAZORA (Castellón)
 TEST REPORT Nº: 51.734
 PAGE Nº: 1 / 2
 DATE OF TEST REPORT: 15/06/2012
 DATE OF RECEIPT OF THE SAMPLE: 08/06/2012
 DATE OF TESTS PERFORMANCE: 08 - 14/05/2012
 NUMBER OF TILES SUPPLIED: 300

DESCRIPTION OF THE SAMPLE:

Glass mosaic, 25 x 25 mm. Ref.:
 -- **Serie "ANTIDESLIZANTE"** --

Code lab.: 221-12

TEST PERFORMED:

- UNE-ENV 12633 : DETERMINATION OF UNPOLISHED FLOORS SLIP RESISTANCE .


 LABORATORIO CERAMICO SEBASTIAN CARPI
 COLEGIO OFICIAL INGENIEROS INDUSTRIALES
 CASTELLÓN

José A. Estibález Catalán
 MANAGER

The samples and his description have been chosen by the petitioner.
 The reported results relate only to the samples tested.
 This report must not be reproduced in part without the written permission of Laboratory.
 The uncertainties have been evaluated according to recommendations of the document ISO/TAG5/WGE : June 95.



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL DE INGENIEROS INDUSTRIALES DE CASTELLON

C.I.F.: Q - 4670001 - I

AVENIDA DEL MAR, Nº 46 - 12003 CASTELLON
TEL: 964 208 583 - FAX: 964 202 594
www.laboratoriocarpi.com

Test report nº: 51.734
Page nº : 2 / 2
Petitioner: VIDREPUR
Date: 15/06/2012

DETERMINATION OF SLIP RESISTANCE (PENDULUM)

DESCRIPTION OF THE SAMPLE.-

Glass mosaic, 25 x 25 mm. Ref.:

-- **Serie "ANTIDESLIZANTE"** --

Code lab.: 221-12

RESULTS.- (Test performed after the **UNE-ENV 12633:2003: Annex A**)

<u>Specimen</u>	<u>Slip resistance</u> (R_d)
1	55
2	54
3	56
4	55

* Average slip resistance: **R_d = 55**

* Average value uncertainty: **U = ± 5 (k=2)**

* Observations.- The classification established on the **SU1** document (Safety of fall risks) of the Technical Code of Building, approved to R.D. 314/2006 , is the next:

<u>CLASSIFICATION OF FLOORS AFTER "SU1"</u>	
<u>Slip resistance</u> (R_d)	<u>Class</u>
$R_d \leq 15$	Class 0
$15 < R_d \leq 35$	Class 1
$35 < R_d \leq 45$	Class 2
$R_d > 45$	Class 3



LABORATORIO CERAMICO SEBASTIAN CARPI
COLEGIO OFICIAL INGENIEROS INDUSTRIALES
CASTELLÓN